

OMEGA apron (PPE - category I)



FIELD OF APPLICATION

OMEGA apron is suitable for use in the food industry (high resistance to animal fats and blood). It is resistant to standard cleaning products. Temperature range for use: -20°C to +40°C.

MATERIAL: Elastomer

FEATURES

- **Colour:** white and blue
- **Thickness:** 350 µm (± 10%)
- **Weight:** 430 g/m² (± 10%)
- Standard **Dimensions** (width x height in cm): 90x115

Aprons with stainless steel brass rings and eyelets.

For standard and harness aprons fittings:

Food safe polypropylene adjustment loop(s).

Detectable plastic hook and polyester braided elastic.



NORMS & REGULATIONS

- Base material in accordance with **EC N° 1935/2004 Regulation**, articles 3 and 4 on materials and articles intended to come into contact with food.
- Base material in accordance with **UE N°10/2011 Regulation** on rubber materials and articles intended to come into contact with food. This PPE may be put in fortuitous contact with all types of food.
- Apron in accordance with **Article 33 of the REACH Regulation N°1907/2006** and its amendments on products containing SVHC.
- Does not contain phthalate, silicone (and silicone derivatives), or bisphenols.



CLEANING CONDITIONS

Cleaning: wash and brush the apron in hot soapy water (40°C) or in a mixture of water and a gentle detergent.

Rinsing: with water. Do not use toxic products to clean or rinse the apron. **Storage:** After cleaning, store in a dark, dry, well-ventilated place. The apron must be replaced when it shows signs of wear and tear.

With a proper use and a good maintenance, your apron lasts longer!

N° intrastat : 40159000

Bien plus que la sécurité
More than just safety

OMEGA apron (PPE - category I)



- This apron complies with the regulation (UE) **PPE 2016/425** and the standard **NF EN ISO 13688** (2013).
- Claimed mechanical properties: abrasion, tear, tensile and puncture resistance.



PERFORMANCE LEVELS

Type of test	Standard	Performance
Abrasion resistance	EN 530 method 2	>2000 cycles
Trapezoidal tear resistance	EN ISO 9073-4	>80 N
Tensile resistance	EN ISO 13934-1	>800N
Puncture resistance	EN 863	>35N

N° intrastat : 62102000

Bien plus que la sécurité
More than just safety